

Technical info Querkus Oak Vintage Retro



1 DESCRIPTION

Type: Panels: top layer real wood veneer (A grade with the chosen look, thickness and touch), MDF core and a balancing layer (A, B+ oak natural or B oak natural grade).

Flex: top layer real wood veneer (A grade) and paper backing.

Thickness: MDF panels: 18 mm, veneer: 0,6 mm^(*)

Splicing method: Mixmatch spliced

Surface structure: Plain, Brushed type B1 or scratched type S1

Each panel is unique, view product pictures on www.querkusdecospan.com.

	TEST METHOD	PANELS
Dimensions		3050x1220x19 or 2500x1240x19 mm
Density	EN323	600-700 kg/m ³
Moisture content panel	EN322	6 % (tolerance: ± 3)
Internal bond	EN319	≥ 0,35 N/mm ²
Bending strength	EN310	≥ 13 N/mm ²
Modulus of elasticity	EN310	≥ 1600 N/mm ²
Formaldehyde	EN171-1	≤ 0,013g/m ³
Deviation of thickness	EN14323	± 0,2 mm
Deviation of length + width	EN14323	± 2 mm
Deviation of squareness	EN324	± 2 mm/m
Flatness	EN14323	2 mm/m
VOC loss	EN664	≤ 3% ppm
PCP content	CEN14823	≤ 5 %
Fire classification	EN13501-1	D-s2-d0

^(*)Keep in mind that this is the thickness of the veneer before we process it. The final thickness may vary.

Samples: Samples can be obtained through www.webshop.decospan.com.

Technical info

Querkus Oak Vintage Retro



3

FLEX

Plain: 3050 x 1240 x 0,6 mm^(*)
Brushed type B1: 2750 x 1220 x 0,6 mm^(*)
Scratched type S1: 2750 x 1220 x 0,6 mm^(*)

^(*)Keep in mind that this is the thickness of the veneer before we process it. The final thickness may vary.

4

OTHER DOCUMENTS

- Technical standards MDF panel
- Querkus brochure
- Pure Wood Charter
- FSC® Certificate

5

CONTACT DETAILS

Decospan NV

Industriezone Grensland

Lageweg 33

8930 Menen – Belgium

T +32 56 52 88 00

E-mail: info@decospan.com

  www.querkusdecospan.com

Decospan NV – Industriezone Grensland – Lageweg 33 – 8930 Menen – Belgium – +32 56 52 88 00 – info@decospan.com
The information is obtained with utmost care and the results are compiled by reliable sources. The herein contained information and data are considered to be accurate and correct, with reservation of misprints, norm errors or other mistakes. Decospan makes no warranty of any kind, expressed or implied, concerning the accuracy or completeness of the information. Decospan will not be liable for claims relating to any party's use of or reliance on information and data contained herein, regardless of whether it is claimed that the info is inaccurate, incomplete or otherwise misleading. No warranty can be derived from this document. It is offered for your consideration, investigation and verification. Due to possible technical changes it is the user's responsibility to obtain the most up to date information.

a product of
DECOSPAN.
Wood Solutions